

Product Data Sheet

Edition 01.2011/v3
 CSC Master Format™ 07 92 13
 Sikasil® WS-295
 Provisional Data Sheet

Sikasil® WS-295

Structural Glazing/Weather Sealing Grade, Neutral-Cure and No-Bleed Silicone Sealant

Description Sikasil® WS-295 is a versatile, one-component, non-sag, elastomeric, neutral-cure silicone sealant. It possesses a no-bleed formulation and is suitable for above grade, horizontal and vertical, interior or exterior applications, including structural glazing and weather sealing.

- Where to Use**
- Structural glazing.*
 - Conventional glazing.
 - Perimeter sealing of windows, doors and skylights.
 - Unitized curtain wall assembly and field installation.
 - Panel stiffeners.
 - Precast expansion joints.
 - Weather sealing of most common building materials.
- * (requires written approval from Sika Canada Technical Services)

- Advantages**
- Structural glazing and weather sealing applications with one product
 - May be applied in below freezing temperatures if substrates are completely dry, frost free and clean.
 - Excellent gunability in all temperatures.
 - Adhesion to porous and non-porous materials, including glass, aluminium, metal, tile, fibreglass, plastic, ceramic, masonry, concrete, brick, powder coated aluminium, fluoropolymer painted surfaces, vinyl, PVC, granite, limestone, marble and wood
 - Capable of accommodating ± 50% joint movement
 - Non-staining, maintains appearance of architectural substrates.
 - Unaffected by most atmospheric conditions.
 - Meets industry specifications: ASTM C920, Type S, Grade NS, Class 50/50, Use NT, M, G, A, O; ASTM C1184 Structural Silicone Sealant; TT-S-00230C, Type II, Class A; CAN/CGSB 19.13-M87, AAMA 802.3 Type II, AAMA 803.3, AAMA 805.2, AAMA 808.3 and California Air Resources Board 2003 requirements for VOC content.

Technical Data

Packaging	295 mL (10.1 US fl. oz) cartridge, 24/case 600 mL (20 US fl. oz) sausage, 20/case			
Colours	Aluminum, Black, Bronze, Colonial White, Limestone, Medium Bronze, White.			
Yield		<u>Linear meters per litre</u>		<u>Linear feet per cartridge</u>
	Width	Depth	Depth	Depth
	mm (in)	13 (1/2)	6 (1/4)	13 (1/2)
	6 (1/4)	24,8	24	
	13 (1/2)	12,4 6,2	12 6	
	19 (3/4)	8,3 4,1	8 4	
Shelf Life	12 months in original, unopened containers when stored at or below 32°C (90°F).			
Application Temperature	Sealant may be applied in below freezing temperatures, but surfaces must be dry, frost free and clean. Sealant should be installed when the joint is at mid-range of its anticipated movement.			
Service Temperature	-62.2 to 176°C (-80 to 350°F)			
Properties at 25°C (77°F) and 50% R.H.				
Uncured Material				
Extrusion Rate g/min ASTM C1183 mod.				
	3 mm (1/8 in) orifice @ 0.6 MPa (90 psi)	150		
	Sealant Slump ASTM D2202	Nil		
	Rheological, Vertical ASTM C639			
	@ 49°C (120°F)	Non-sag		
	Skin-Over Time	25 min		
	Tack-Free Time ASTM C679	50 min		
	Cure Rate	3 mm (1/8 in) / 24 hrs		
Cured Material (21 days @ 25°C (77°F) and 50% R.H.)				
	Movement Capability ASTM C719	±50%		
	Elongation at Break ASTM D412	800%		
	100% Modulus ASTM D412	0.38 MPa (55 psi)		
	Shore A Hardness ASTM C661	20		
	Tensile Strength ASTM D412	1.59 MPa (230 psi)		



Peel Strength ASTM C794	5.38 kg/cm (30 pli) average
Staining ASTM C1248 (granite, marble, limestone, brick and concrete)	Passes
Accelerated Weathering (QUV) 10 000 hours	No change
Test results are averages obtained under laboratory conditions. Reasonable variations can be expected.	

How to Use

Joint Detailing

The number of joints and the joint width should be designed for a recommended joint movement of +50% and -50% at time of installation.

The depth of the sealant should be 1/2 the width of the joint. The minimum sealant depth is 6 mm (1/4 in), the maximum is 13 mm (1/2 in).

To control the sealant depth, use a closed cell polyethylene, non-gassing polyolefin or open cell polyurethane backer rod. Closed cell backer rod should be 25% larger than joint width; do not compress more than 40%. Open cell should be compressed 40%. Do not use open cell rod in horizontal on grade joint or with EIFS.

If the joint depth does not allow for a backer rod, use polyethylene bond breaker tape to prevent three-sided adhesion

Surface Preparation

All joint surfaces must be clean, sound, dry, and frost free. Joint walls must be free of oils, asphalt, tar, bituminous materials, grease, paints, coatings or sealers. Curing compounds, release agent residues, glazing compounds, and any other foreign matter must be removed.

Porous substrates should be cleaned by mechanical methods, such as grinding, saw cutting, blast cleaning (sand or water), or wire brushing. Dust, loose particles, etc. should be blown out of joints with oil-free compressed air or vacuum cleaned to remove all material which may interfere with adhesion.

Non-porous substrates should be cleaned by using a solvent wipe method, applied by lint free and clean rags and allow the solvent to evaporate before installing the sealant. Xylene or an approved commercial solvent can be used, ensuring the solvent manufacturer's instructions are strictly followed. Soap or detergent and water cleaning treatments are not recommended. Cleaning of all surfaces should be done just prior to the sealant application.

Apply Sikasil® WS-295 only to suitably prepared and cleaned substrates. Long term adhesion and performance is dependant upon such.

Priming

Sikasil® WS-295 is designed to obtain adhesion without the use of a primer, however, certain substrates may require a primer. A field test is recommended to determine the adhesion of the sealant and/or primer and sealant combination, to confirm results and the suitability of the proposed application. Consult Sikasil® Primer Data Sheets or contact Sika Canada Technical Services for additional information on priming.

NOTE: Priming is never a substitute for proper surface cleaning and preparation.

Application

For best performance Sikasil® WS-295 should be gunned into joints when the joint slot is at the mid-point of its designed expansion and contraction.

Do not open the product container until preparation and, where necessary, priming work has been completed.

When installing during time of large temperature fluctuations, such as spring or fall, and in joints designed for movement greater than ±25%, be aware that significant joint movement before cure, may cause aesthetic issues such as ripples in the sealant surface. Performance will not be affected

Apply the sealant using a professional caulking gun or dispensing equipment. Place the nozzle deep into the joint and gun with a steady and even flow of sealant preceding the nozzle to avoid air entrapment. Also avoid overlapping of the sealant as this also entraps air. Extrude in one continuous operation with consistent positive pressure to force the material into the joint.

Tool the sealant at once after application and before a skin forms (approximately 25 minutes). Tool to a concave shape and ensure adequate pressure to achieve maximum adhesion with the joint walls. Dry tooling is recommended.

Note: Do not use spray water or other liquids when tooling.



Clean Up	Clean all tools and equipment and remove excess sealant from substrates, all while the material is uncured, using a commercial solvent, such as xylene. Strictly follow the manufacturer's instructions for use and warnings. Once hardened, product can only be removed mechanically. Wash soiled hands and skin thoroughly in hot soapy water or use Sika® Hand Cleaner towels.
Limitations	<ul style="list-style-type: none">■ Requires written approval from Sika Canada Technical Services prior to use in structural glazing.■ The minimum sealant depth is 6 mm (1/4 in), the maximum is 13 mm (1/2 in).■ Do not apply when substrate temperatures are below -28°C (-20°F) or above 54°C (130°F).■ Lower temperature and humidity will extend tack free and cure rates.■ Do not apply to damp or wet surfaces.■ Substrates must be completely dry, frost free, and clean.■ Do not apply to surfaces that are to be painted, as the sealant surface will not hold paint.■ Do not apply to substrates that bleed oil, plasticizers or solvent.■ Do not allow the uncured sealant to come in contact with solvent or curing polyurethanes.■ Avoid contact with materials or surfaces impregnated with, or containing oil, asphalt, tar, or bituminous materials.■ This material is not intended for immersion or vehicular traffic.■ Brass and copper may be discoloured through contact: apply a sample prior to application.■ Test sensitive substrates, such as mirror backings, for compatibility before use.■ Allow treated wood to age for at least six months before application of the sealant.
Caution	Avoid contact with skin and eyes. Can cause an allergic reaction and sensitization. Avoid inhaling the vapours during curing. Consult product label for additional information.
First Aid	In case of skin contact, wash with soap and water. For eye contact, flush immediately with plenty of water for at least 15 minutes. Contact a physician. For respiratory problems, transport victim to fresh air. Remove contaminated clothing and wash before re-use.

For more information, consult Sika Material Safety Data Sheet.

KEEP OUT OF REACH OF CHILDREN
FOR INDUSTRIAL USE ONLY

The information, and in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions, within their shelf life. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any recommendations, or from any other advice offered. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users should always refer to the most recent issue of the Product Data Sheet for the product concerned, copies of which will be supplied on request or can be accessed in the Internet under www.sika.ca.

Sika Canada Inc.

Quebec

601 Delmar Avenue
Pointe-Claire, QC H9R 4A9
Tel.: 514-697-2610
Fax: 514-697-3087

Ontario

6915 Davand Drive
Mississauga, ON L5T 1L5
Tel.: 905-795-3177
Fax: 905-795-3192

Alberta

18131-114th Avenue N.W.
Edmonton, AB T5S 1T8
Tel.: 780-486-6111
Fax: 780-483-1580

1-800-933-SIKA
www.sika.ca

An ISO 9001 certified company
Pointe-Claire : ISO 14001 certified EMS



Construction

